





Technical data sheet

Total thickness: **0.17mm**


BS FIX 220.012 TW

Main carrier:	TRANSPARENT PET FILM
Secondary carrier:	-
Main liner:	WHITE SILICONE GLASSINE PAPER
Secondary liner:	-
Open side adhesive:	PURE ACRYLIC
Closed side adhesive:	PURE ACRYLIC





Adhesive properties

Peel 90° on steel		Open side	14	M.U.	Method
		Closed side	14	N/25 mm	BS 35 - AFERA 5001
Rolling ball test		Open side	2	M.U.	Method
		Closed side	2	Cm	BS 12 - PSTC-6
Quick stick on steel		Open side	20	M.U.	Method
		Closed side	20	N/25 mm	BS 6 - AFERA 4015
Shear on steel		Open side	20	M.U.	Method
		Closed side	20	Hours	BS 68 - AFERA 5012

Temperature resistance

Long term		120	M.U.: °C
Short term		160	M.U.: °C

Mechanical properties

Tensile strength at break Longitudinal		Min.	Max.	M.U.	Method
		2000	3000	Kg/cm2	ASTM D 882
Tensile strength at break Transversal		Min.	Max.	M.U.	Method
		2000	3000	Kg/cm2	ASTM D 882
Elongation at break Longitudinal		Min.	Max.	M.U.: %	Method
		90	170		ASTM D 882
Elongation at break Transversal		Min.	Max.	M.U.: %	Method
		90	160		ASTM D 882

Technical data sheet

Total thickness: **0.17mm**

BS FIX 220.012 TW

Description

The product is made up of a calibrated thickness polyester cloth carrier and a white silicone glassine paper liner.

The acrylic adhesive system, on both sides, provides high adhesion and initial tack, allowing optimum adhesion on irregular and flat surfaces.

Applications

Ideal for flying splice application of plastic materials that are normally difficult to adhesivize because they are slippery and / or have low surface tension.

Recommended for a wide variety of materials: irregular surfaces, plastics, metal profiles, decorative coatings.

The product guarantees a permanent bond on foams, insulating coatings, paper, plastic, metals, sail fabrics and composite materials subject to a wide range of environmental conditions.

Product PLUS

High initial tack.

Good resistance to thermal stress and UV rays exposure.

Recommendations for correct use

Storage

For a proper storage of the product we recommend to keep the product in the original package until it is needed and use it within 12 months from delivery.

The storage shall be carried out at a room temperature between 15°C and 27°C, and a relative humidity < 60%.

Once removed from the packaging, place the product vertically and protect it from dust. Do not expose product and packaging to direct sunlight and heat sources.

Surface cleaning

The product shall be applied on sufficiently flat surfaces and with no non-stick coating.

In order to obtain a correct product adhesion level on surfaces, it is indispensable that the surfaces are properly cleaned before the application. It is recommended to use quick-evaporating solvents.

After cleaning make sure that the solvent has completely evaporated, by waiting for a sufficiently long period of time or by drying the surface with a completely dry cloth.

Application

As adhesive tape is pressure-sensitive, it is necessary a proper pressing pressure on the back of the tape, once applied on the surface, to ensure the grip of the adhesive and a full lamination.

Measuring tolerances

The tape cutting width tolerance can vary within a range of ± 0.7 mm. Tighter tolerances for specific formats and measures can be available on request.

Disposal

It is recommend to dispose the product after use according to the specific regulations of the country it was used in.

For additional information, please refer to our Technical Office:

info.tapes@biesSseworld.com
+39 02 90 11 11 18