


Technical data sheet

Total thickness (carrier + adhesive): **1.5mm**

# MS FOAM 1500 PET

Main carrier:	BLUE PE FOAM
Secondary carrier:	WHITE PET FILM
Main liner:	-
Secondary liner:	-
Open side adhesive:	-
Closed side adhesive:	PURE ACRYLIC

**Adhesive properties**

<b>Peel 180° on steel</b>		Open side	-	M.U.	Method
		Closed side	-	N/25 mm	-
<b>Rolling ball test</b>		Open side	-	M.U.	Method
		Closed side	-	Cm	-
<b>Quick stick on steel</b>		Open side	-	M.U.	Method
		Closed side	-	N/25 mm	-
<b>Shear on steel</b>		Open side	-	M.U.	Method
		Closed side	-	Hours	-

**Temperature resistance**

<b>Long term</b>		-	M.U.: °C
<b>Short term</b>		-	M.U.: °C

**Mechanical properties**

<b>Tensile strength at break Longitudinal</b>		Min.	Max.	M.U.	Method
		1914	1914	-	ISO 1926
<b>Tensile strength at break Transversal</b>		Min.	Max.	M.U.	Method
		1616	1616	-	ISO 1926
<b>Elongation at break Longitudinal</b>		Min.	Max.	M.U.: %	Method
		450	450	-	ISO 1926
<b>Elongation at break Transversal</b>		Min.	Max.	M.U.: %	Method
		477	477	-	ISO 1926

Note: All above information are believed to be true and reliable but they are given only for guidance. They do not constitute a warranty or a specification. The characteristics refer to average values, relevant to samples collected from our production. Users must confirm the suitability of the products through their own tests. BiesSse Tape reserve the right to introduce at any moment and without warning those changes that they deem necessary. Tolerance of Technical Data: ± 30%

## Technical data sheet

Total thickness (carrier + adhesive): **1.5mm**

# MS FOAM 1500 PET

### Description

The product is made up of a high quality closed-cells physically cross-linked blue expanded polyethylene foam carrier, laminated with a white polyester film (Mylar).

Foam width: 1280 mm  
Mylar width: 1400 mm (60 mm+60 mm)

### Applications

Ideal for high quality corrugated postprint.

Ideal for mounting operations on steel cylinders with coupling plastic profile.

Suitable for different plate thickness.

Reccomended to reduce dot gain and washboard effects.

### Product PLUS

Excellent slipping on the printing cylinder.

Optimal resilience and high compression stability even at high print speeds to avoid cardboard crushing.

## Recommendations for correct use

### Storage

For a proper storage of the product we recommend to keep the product in the original package until it is needed and use it within 12 months from delivery.

The storage shall be carried out at a room temperature between 15°C and 27°C, and a relative humidity < 60%.

Once removed from the packaging, place the product vertically and protect it from dust. Do not expose product and packaging to direct sunlight and heat sources.

### Surface cleaning

The product shall be applied on sufficiently flat surfaces and with no non-stick coating.

In order to obtain a correct product adhesion level on surfaces, it is indispensable that the surfaces are properly cleaned before the application. It is recommended to use quick-evaporating solvents.

After cleaning make sure that the solvent has completely evaporated, by waiting for a sufficiently long period of time or by drying the surface with a completely dry cloth.

### Application

As adhesive tape is pressure-sensitive, it is necessary a proper pressing pressure on the back of the tape, once applied on the surface, to ensure the grip of the adhesive and a full lamination.

### Measuring tolerances

The tape cutting width tolerance can vary within a range of  $\pm 0.7$  mm. Tighter tolerances for specific formats and measures can be available on request.

### Disposal

It is recommend to dispose the product after use according to the specific regulations of the country it was used in.

For additional information, please refer to our Technical Office:  
**info.tapes@biesSseworld.com**  
**+39 02 90 11 11 18**